



Laser Crystal

Nd:YAG

Invented in the sixties of the last century, Nd:YAG has been and continue to be the most widely used laser crystal for solid-state crystal material. Its laser parameters are a good compromise between the strengths and weaknesses of its competition. Nd:YAG crystals are used in all types of solid-state lasers. Compared with others laser crystals, its fluorescence lifetime is twice more than Nd:YVO4, and thermal conductivity is also better.

Specifications

Nd Dopant Level	0.5 - 1.1 atm%
Orientation	<111> crystalline direction ($\pm 0.5\text{deg}$)
Dimension Tolerances	Diameter: $\pm 0.05\text{mm}$ Length: $\pm 0.5\text{mm}$
Surface Quality	10/5 Scratch and Dig
Clear Aperture	>90%
Surface Flatness	$< \lambda/10@633\text{nm}$
Wavefront Distortion	$< \lambda/8@633\text{nm}$
Parallelism	<10 arc seconds
Perpendicularity	<5 arc minutes
Chamfer	<0.1mm@45deg
AR Coating	Reflectivity R<0.25%@1064nm per surface Damage threshold over 750MW/cm ² @1064nm, 10ns and 10Hz
HR Coating	Standard R>99.8%@1064nm and R<5%@808nm
Extinction Ratio	Rods with diameter from 3mm to 6.35mm and with length to 100mm: >30dB Rods with diameter from 7mm to 10mm and with length to 100mm: >28dB



Standard Product-Nd:YAG

Part No.	Diameter(mm)	Length(mm)	Doping(%)	End Wedge (Deg)	Coating
NYG9003-65	3.0	65.0	0.6	0/0	AR/AR@1064nm
NYG9003-78	3.0	78.0	0.6	0/0	AR/AR@1064nm
NYG9102-25	2.0	25.0	1.0	0/0	AR/AR@1064nm
NYG9103-50	3.0	50.0	1.0	0/0	AR/AR@1064nm
NYG9103-65	3.0	65.0	1.0	0/0	AR/AR@1064nm
NYG9104-50	4.0	50.0	1.0	0/0	AR/AR@1064nm
NYG9104-120	4.0	120.0	1.0	0/0	AR/AR@1064nm
NYG9105-85	5.0	85.0	1.0	0/0	AR/AR@1064nm
NYG9106-120	6.0	120.0	1.0	0/0	AR/AR@1064nm
NYG9107-120	7.0	120.0	1.0	0/0	AR/AR@1064nm
NYG9107-145	7.0	145.0	1.0	0/0	AR/AR@1064nm
NYG9107-155	7.0	155.0	1.0	0/0	AR/AR@1064nm
NYG9107-165	7.0	165.0	1.0	0/0	AR/AR@1064nm
NYG9107-185	7.0	185.0	1.0	0/0	AR/AR@1064nm
NYG9108-100	8.0	100.0	1.1	0/0	AR/AR@1064nm
NYG9108-145	8.0	145.0	1.0	0/0	AR/AR@1064nm
NYG9108-155	8.0	155.0	1.0	0/0	AR/AR@1064nm
NYG9108-165	8.0	165.0	1.0	0/0	AR/AR@1064nm
NYG9108-185	8.0	185.0	1.0	0/0	AR/AR@1064nm

Grooved Nd:YAG

Compared with the common Nd:YAG laser rods, the grooved Nd:YAG laser rods has the following advantages.

- The quality of the beam has been improved
- Thermal effect has been reduced
- The efficiency of Grooved Rod has been improved by 10%-20%



Specifications

Nd Dopant Level	0.5 - 1.1 atm%
Orientation	<111> crystalline direction ($\pm 0.5\text{deg}$)
Dimension Tolerances	Diameter: $\pm 0.05\text{mm}$ Length: $\pm 0.5\text{mm}$
Surface Quality	10/5 Scratch and Dig
Clear Aperture	>90%
Surface Flatness	$< \lambda/10@633\text{nm}$
Wavefront Distortion	$< \lambda/8@633\text{nm}$
Parallelism	<10 arc seconds
Perpendicularity	<5 arc minutes
Chamfer	<0.1mm@45deg
AR Coating	Reflectivity R<0.25%@1064nm per surface Damage threshold over 750MW/cm ² @1064nm, 10ns and 10Hz Other coating is per your request
Extinction Ratio	Rods with diameter from 3mm to 6.35mm and with length to 100mm: >30dB Rods with diameter from 7mm to 10mm and with length to 100mm: >28dB



Diffusion Bonded Cr:YAG+Nd:YAG Rod

The diffusion bonded Cr:YAG+Nd:YAG Rod consists of one Nd:YAG crystal and one or two Cr:YAG absorber. They are combined by optical contact method and further bonded under high temperature. The diffusion bonded Cr:YAG+Nd:YAG Rod helps to decrease thermal lens effect considerably in high power solid state Laser.

- Improve beam quality
- High damage threshold
- Decrease thermal effect
- Improve efficiency
- Compact size



Capabilities

Nd:YAG Doping	0.4-1.1%
Intrinsic Loss	0.1%/cm ¹
Scattering Sites	invisible, probed with a He-Ne laser
Diameter Tolerance	+0/-0.02mm
Length Tolerance	+0.5/-0mm
Surface Quality	10/5 Scratch and Dig
Clear Aperture	>95%
Surface Flatness	<λ/10@632.8nm
Wavefront Distortion	<λ/10@632.8nm
Parallelism	<10 arc seconds
Perpendicularity	<5 arc minutes
Chamfer	0.1mm@45°
Barrel Finish	Ground Finish with 400# Grit

Nd:YVO₄

Nd:YVO₄ crystal is one of the most efficient laser host crystal currently existing for diode laser pumped solid state lasers. Its large stimulated emission cross-section at lasing wavelength, high absorption coefficient and wide absorption bandwidth at pump wavelength, high laser induced damage threshold as well as good physical, optical and mechanical properties make Nd:YVO₄ an excellent crystal for high power, stable and cost effective diode pumped solid-state lasers.

- Low lasing threshold and high slope efficiency
- Low dependency on pump wavelength
- Large stimulated emission cross-section at lasing wavelength
- High absorption over a wide pumping wavelength bandwidth
- Optically uniaxial and large birefringence emits polarized laser



Specifications

Nd Dopant Level	0.1 - 5.0 atm%
Scattering	Invisible, probed with a He-Ne laser
Orientation Tolerance	±0.5deg
Dimension Tolerance	±0.1mm
Surface Quality	10/5 Scratch and Dig
Clear Aperture	>90%
Surface Flatness	<λ/10@633nm
Wavefront Distortion	<λ/8@633nm
Parallelism	<10 arc seconds
End-faces Configuration	Plano/Plano
Coating	AR1064&HT808: R<0.1%@1064nm, R<5%@808nm HR1064&HT808&HR532: R>99.8%@1064nm, R<5%@808nm, R>99%@532nm AR1064: R<0.1%@1064nm

Nonlinear Crystal

BBO

BBO (beta-BaB₂O₄) is a nonlinear optical crystal which combines a number of unique features. These features include wide transparency and phase matching ranges, large nonlinear coefficient, high damage threshold and excellent optical homogeneity. Therefore, BBO provides an attractive solution for various nonlinear optical applications.

BBO crystal is also an excellent electro-optic crystal for high power applications at the wavelength range from 200nm to 2500nm. It can be used for Q-Switching in a CW diode pumped Nd:YAG laser with average power>50W.




Main Features

- Good mechanical and physical properties
- Broad phase-matchable second-harmonic-generation (SHG) range from 409.6 nm to 3500 nm
- Wide transmission region from 190 nm to 3500 nm
- Large effective SHG coefficient
- High damage threshold of 10 GW/cm² for 100 ps pulse-width at 1064 nm
- High optical homogeneity with Δn=10⁻⁶/cm
- Wide temperature-bandwidth of about 55°C (for type I SHG 1064 nm)

Typical Applications

- Second, third, fourth and fifth harmonic generation of Nd:YAG and Nd:YLF laser
- Frequency-doubling, -tripling and -mixing of Dye lasers
- Second, third and fourth harmonic generation of Ti:Sapphire and Alexandrite lasers
- Optical parametric amplifier (OPA) and optical parametric oscillators (OPO)
- Frequency-doubling of Argon ion, Cu-vapor and Ruby lasers
- Research and development for advanced laser techniques, including all-solid state wide-tunable lasers, ultrafast pulse lasers, and DUV lasers



Standard Parameter for Different Application

Harmonic generations of Nd:YAG lasers

1064nm SHG-> 532nm	4x4x7mm	Type I, Theta=22.8deg, Phi=0deg
1064nm THG-> 355nm	4x4x7mm	Type I, Theta=31.3deg, Phi=0deg
1064nm THG-> 355nm	4x4x7mm	Type II, Theta=38.6deg, Phi=30deg
1064nm 4HG-> 266nm	4x4x7mm	Type I, Theta=47.6deg, Phi=0deg
1064nm 5HG-> 213nm	4x4x7mm	Type I, Theta=51.1deg, Phi=0deg

Frequency doubling of dye lasers

670-530nm SHG-> 355-260nm	8x4x7mm	Type I, Theta=40deg, Phi=0deg
600-440nm SHG-> 300-220nm	8x4x7mm	Type I, Theta=55deg, Phi=0deg
444-410nm SHG-> 222-205nm	8x4x7mm	Type I, Theta=80deg, Phi=0deg

OPO and OPA pumped by harmonics of Nd:YAG lasers

532nm Pump-> 680-2600nm	4x4x12mm	Type I, Theta=21deg, Phi=0deg
355nm Pump-> 410-2600nm	6x4x12mm	Type I, Theta=30deg, Phi=0deg
355nm Pump-> 410-2600nm	7x4x15mm	Type II, Theta=37deg, Phi=30deg
266nm Pump-> 295-2600nm	6x4x12mm	Type I, Theta=39deg, Phi=0deg

Harmonic generations of Ti:Sapphire lasers

700-1000nm SHG-> 350-500nm	7x4x7mm	Type I, Theta=28deg, Phi=0deg
700-1000nm THG-> 240-330nm	8x4x7mm	Type I, Theta=42deg, Phi=0deg
700-1000nm FHG-> 210-240nm	8x4x7mm	Type I, Theta=66deg, Phi=0deg

Frequency doubling and tripling of Alexandrite lasers

720-800nm SHG-> 360-400nm	4x4x7mm	Type I, Theta=31deg, Phi=0deg
720-800nm THG-> 240-265nm	4x4x7mm	Type I, Theta=48deg, Phi=0deg

Intracavity SHG of Ar+ laser with Brewster angle cut BBO

514nm SHG-> 257nm	4x4x7mm	Type I, Theta=51deg, Phi=0deg
488nm SHG-> 244nm	4x4x7mm	Type I, Theta=55deg, Phi=0deg

Specifications

Dimension Tolerance	(W±0.1mm) x (H±0.1mm) x (L±0.2mm)
Angle Tolerance	Δθ<0.5°, ΔΦ<0.5°
Surface Quality	20/10
Clear Aperture	>90%
Surface Flatness	<λ/8@633nm
Wavefront Distortion	<λ/4@633nm
Parallelism	<20 arc seconds
Perpendicularity	<5 arc minutes

Standard Product-BBO

Part No.	Dimension(mm)	θ (°)	Φ (°)	Coating	Application
BBO9001	4.0*4.0*7.0	22.8	0	AR/AR@1064&532nm	SHG@1064, Type I
BBO9002	4.0*4.0*7.0	47.6	0	AR/AR@532&266nm	4HG@1064, Type I
BBO9003	4.0*4.0*10.0	22.8	0	AR/AR@1064&532nm	SHG@1064, Type I
BBO9004	4.0*4.0*10.0	47.6	0	AR/AR@532&266nm	4HG@1064, Type I
BBO9005	5.0*5.0*2.0	29.2	0	AR/AR@800&400nm	SHG@800, Type I
BBO9006	5.0*5.0*1.0	29.2	0	AR/AR@800&400nm	SHG@800, Type I
BBO9007	5.0*5.0*0.3-0.5	29.2	0	AR/AR@800&400nm	SHG@800, Type I
BBO9008	5.0*5.0*0.1	29.2	0	AR/AR@800&400nm	SHG@800, Type I

KTP

Potassium Titanium Oxide Phosphate (KTiOPO₄), or KTP, is an efficient nonlinear optical crystal in the visible to infrared spectral region with relatively low cost. It has large nonlinear coefficient. The effective nonlinear optical coefficient of KTP deff at 1064nm is more than 1.5 times that of BBO.



Main Features

- Wide Angular Bandwidth and Small Walk-off Angle
- Broad Temperature and Spectral Bandwidth
- High Electro-Optic (E-O) Coefficient and Low Dielectric Constant
- Large Figure of Merit for an Optical Waveguide Modulator
- Nonhygroscopic, Good Chemical and Mechanical Properties
- Efficient frequency conversion(1064nm SHG is about 80%)
- Large nonlinear optical coefficients
- High thermal conductivity
- Minimum mismatch gradient
- Low cost compare with BBO and LBO

Typical Applications

- Frequency Mixing (SFM) of Nd Laser and Diode Laser for Blue Output
- Frequency Doubling (SHG) of Nd-doped Lasers for Green/Red Output
- Parametric Sources (OPG, OPA and OPO) for 0.6um-4.5um Tunable Output
- E-O Modulators, Optical Switches, Directional Couplers
- Optical Waveguides for Integrated NLO and E-O Devices

Specifications


Angle Tolerance	Δθ<0.5°, Δφ<0.5°
Dimension Tolerance	±0.1mm
Surface Quality	10/5 Scratch and Dig
Clear Aperture	>95% central area
Flatness	<λ/8@633nm
Wavefront Distortion	<λ/4@633nm
Parallelism	<20 arc seconds
Perpendicularity	<15 arc minutes
Residual Reflectivity	<0.2% at 1064nm and <0.5% at 532nm per surface
Quality Warranty Period	One year under proper use
Coating	AR/AR@1064&532nm: S1&S2 AR@1064&532nm, R<0.25%@1064nm, R<0.5%@532nm HR/AR@1064&532nm: S1 HR@1064nm&HT@532nm, R>99.8%@1064nm, R<5%@532nm S2 AR@1064&532nm, R<0.25%@1064nm, R<0.5%@532nm



Passive Q-Switch Crystal

Cr:YAG

Cr³⁺:Y₃Al₅O₁₂ crystal is one of the most promising passive Q-switching materials for passively Q-switching diode pumped or lamped Nd or Yb doped lasers at wavelength from 0.8 to 1.2μm. Because of its chemical stability, durability, UV resistance, good thermal conductivity, high damage threshold (> 500 MW/cm²) and easy operation, it will replace some traditional switching materials, such as LiF and organic Dye. The preliminary experiments of Cr:YAG showed that the pulse width of passively Q-switched lasers could be as short as 9 ns for diode pumped Nd:YAG lasers and repetition rate as high as 10kHz for diode pumped Nd:YVO₄ lasers.



Specifications

Dimension	Diameter: 3~12mm H×W: 2×2~30×30mm
Initial Transmission	5%~95%@1064nm
Dimension Tolerance	±0.1mm
Surface Quality	20/10 Scratch and Dig
Clear Aperture	>90%
Surface Flatness	<λ/10@633nm
Parallelism	<20 arc seconds
Perpendicularity	<5 arc minutes
AR Coating	<0.25%@1064nm

Standard Product-Cr:YAG

Part No.	Diameter(mm)	Transmission(%)	Coating
CYG9006-30	6.0	30	AR/AR@1064nm
CYG9006-40	6.0	40	AR/AR@1064nm
CYG9006-50	6.0	50	AR/AR@1064nm
CYG9006-60	6.0	60	AR/AR@1064nm
CYG9006-70	6.0	70	AR/AR@1064nm
CYG9006-75	6.0	75	AR/AR@1064nm
CYG9006-80	6.0	80	AR/AR@1064nm
CYG9006-85	6.0	85	AR/AR@1064nm
CYG9010-30	10.0	30	AR/AR@1064nm
CYG9010-40	10.0	40	AR/AR@1064nm
CYG9010-50	10.0	50	AR/AR@1064nm
CYG9010-60	10.0	60	AR/AR@1064nm
CYG9010-70	10.0	70	AR/AR@1064nm
CYG9010-75	10.0	75	AR/AR@1064nm
CYG9010-80	10.0	80	AR/AR@1064nm
CYG9010-85	10.0	85	AR/AR@1064nm

E-O Crystal

BBO

BBO crystal is an excellent electro-optic crystal for high power applications at the wavelength range from 200nm to 2500nm. BBO has a high damage threshold and a low dielectric constant and is useful in high repetition rate, high average power (up to 150W) diode pumped solid state lasers (DPSS lasers). BBO has significant advantages over other materials in terms of laser power handling abilities, temperature stability, and substantial freedom from piezoelectric ringing.



Specifications


Dimensional Tolerance	±0.1mm
Angle Tolerance	±0.5deg
Surface Quality	20/10 Scratch and Dig
Clear Aperture	>90%
Surface Flatness	<λ/8@633nm
Wavefront Distortion	<λ/4@633nm
Parallelism	<20 arc seconds
Perpendicularity	<5 arc minutes
Coating	Per your request

Standard Product-BBO

Part No.	Dimension(mm)	Cut Angle	End Face	Side Face
BBO9320	3.0*3.0*20.0	Z-cut	AR/AR@1064nm	Au Electrodes
BBO9420	4.0*4.0*20.0	Z-cut	AR/AR@1064nm	Au Electrodes
BBO9620	6.0*6.0*20.0	Z-cut	AR/AR@1064nm	Au Electrodes
BBO9820	8.0*8.0*20.0	Z-cut	AR/AR@1064nm	Au Electrodes
BBO9120	10.0*10.0*20.0	Z-cut	AR/AR@1064nm	Au Electrodes

LiNbO₃

Lithium Niobate (LiNbO₃) is widely used as electro-optic modulator and Q-switch for Nd:YAG, Nd:YLF and Ti:Sapphire lasers as well as modulator for fiber optics, etc. The transverse modulation is mostly employed for LiNbO₃ crystal. The light propagates in z-axis direction and electrodes are applied to x faces.



Specifications

Dimensional Tolerance	±0.1mm
Angle Tolerance	±0.5°
Surface Quality	20/10
Clear Aperture	>90%
Surface Flatness	<λ/8@633nm
Wavefront Distortion	<λ/4@633nm
Parallelism	<20arc seconds
Perpendicularity	<5arc minutes
AR Coating	R<0.25%@1064nm

Standard Product-LiNbO₃

Part No.	Dimension(mm)	Cut Angle	End Face	X Face
LNO9315	3.0*3.0*15.0	Z-cut	AR/AR@1064nm	Au Electrodes
LNO9415	4.0*4.0*15.0	Z-cut	AR/AR@1064nm	Au Electrodes
LNO9625	6.0*6.0*25.0	Z-cut	AR/AR@1064nm	Au Electrodes
LNO9925	9.0*9.0*25.0	Z-cut	AR/AR@1064nm	Au Electrodes

Laser Crystal

Nonlinear Crystal

Passive Q-Switch Crystal

E-O Crystal

Birefringent Crystal



Birefringent Crystal

YVO₄


The yttrium orthovanadate (YVO₄) is a positive uniaxial crystal grown with Czochralski method. It has good mechanical and physical properties and is ideal for optical polarizing components due to its wide transparency range and large birefringence. It is an excellent synthetic substitute for Calcite (CaCO₃) and Rutile (TiO₂) crystals in fiber optical applications such as isolators, circulators, beam displacers, Glan polarizers and other polarizing optics.



Calcite


Calcite is a negative uniaxial crystal that has high birefringence, wide spectral transmission and availability in reasonably sized rhombs.

Although is a fairly soft crystal and is easily scratched, it is ideal material used as visible and near IR polarizers, such as Glan Thompson, and Glan Taylor Glan laser.



LiNbO₃

Lithium Niobate (LiNbO₃) is widely used in fiber communication devices as Birefringent crystal. It has good mechanical and physical properties and is ideal for optical polarizing components due to its wide transparency range and low cost. It is an excellent material in fiber communication applications such as isolators, circulators, beam displacers, and other polarizing optics.



a-BBO

High temperature form BBO (α-BaB₂O₆) is an excellent negative uni-axial birefringent crystal. It has large birefringence coefficient and good transmission over a broad range, from 189nm to 3500nm. Unlike β-BBO, α-BBO is not useful for NLO application due to the centric symmetry with its crystal structure.

A-BBO is excellent crystal in Glan Taylor, Glan Laser and Glan Thompson polarizer as well as walk-off beamsplitters, especially for high power and UV polarizers. This is due to their unique UV transparency, good mechanical properties and high damage threshold. Union Optic manufactures many Glan polarizers and beam displacers from high quality α-BBO crystals for UV and high power operations.




Quartz

Single Synthetic Crystal Quartz is grown by hydrothermal method in autoclaves. It has trigonal crystal structure with right-handed or left-handed modification. Quartz crystals have low stress birefringence and high refractive index homogeneity. The optical transmission range of crystal quartz is 0.2-2.5microns. Due to its piezoelectric properties, low thermal expansion, good mechanical parameters and excellent optical characteristics, crystal quartz is widely used in electronics, precision and laser optics, fiber communications, X-ray optics, pressure sensors and etc.



MgF₂

Magnesium Fluoride (MgF₂) is good birefringent crystal with good transmission over 120-7000nm. It is a hard material which is resistant to thermal and mechanical shock and can be worked according to the highest standards. MgF₂ single crystals is a positive birefringent crystal and widely used for Optical prisms, lenses, windows and other optical components.



Capabilities

Dimension Tolerance	(W±0.1mm) x (H±0.1mm) x (L±0.2mm)
Optical Axis Orientation	±0.5°
Surface Quality	20/10
Clear Aperture	>90%
Surface Flatness	<λ/4@633nm
Parallelism	<15arc seconds
Perpendicularity	<10arc minutes
AR-Coating	Per Your Request

Capabilities

Dimension Tolerance	±0.1mm
Optical Axis Orientation	±0.5°
Surface Quality	20/10
Clear Aperture	>90%
Surface Flatness	<λ/4@633nm
Wavefront Distortion	<λ/2@633nm
Parallelism	<15arc seconds
Perpendicularity	<10arc minutes
AR-Coating	Per Your Request

Capabilities

Dimension Tolerance	±0.1mm
Optical Axis Orientation	±0.5°
Surface Quality	20/10
Clear Aperture	>90%
Surface Flatness	<λ/8@633nm
Wavefront Distortion	<λ/4@633nm
Parallelism	<20arc seconds
Perpendicularity	<5arc minutes
AR-Coating	Per Your Request

Capabilities

Dimension Tolerance	±0.1mm
Optical Axis Orientation	±0.5°
Surface Quality	20/10
Clear Aperture	>90%
Surface Flatness	<λ/4@633nm
Wavefront Distortion	<λ/2@633nm
Parallelism	<15arc seconds
Perpendicularity	<3arc minutes
AR-Coating	Per Your Request

Capabilities

Dimension Tolerance	±0.1mm
Optical Axis Orientation	±0.5°
Surface Quality	20/10
Clear Aperture	>90%
Surface Flatness	<λ/8@633nm
Wavefront Distortion	<λ/10@633nm
Parallelism	<1arc seconds
AR-Coating	Per Your Request

Capabilities

Dimension Tolerance	±0.1mm
Optical Axis Orientation	±0.5°
Surface Quality	20/10
Clear Aperture	>90%
Surface Flatness	<λ/4@633nm
Wavefront Distortion	<λ/4@633nm
Parallelism	<15arc seconds
AR-Coating	Per Your Request